



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 10/08/2022**

**TO: 10/08/2023**

LAB. ID NUMBER: 52853  
POWDER COATING: DS-0733S  
HEAT TRANSFER FILM: 2304/08  
colour variation ( $\Delta E$ ): 1,21  
residual gloss: 100%

### Technical Remarks

Excellent residual gloss and normal color variation  
( $\Delta E$ )

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

