



EXPOSURE PERIOD:

FROM: 20/04/2015

TO: 09/05/2016

LAB. ID NUMBER: 36684
POWDER COATING: DS 1401
HEAT TRANSFER FILM: 1401/01
Colour variation (ΔE): 1,78
residual gloss: 100%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS
The residual gloss shall be at least 50% of the original gloss.
The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

