
 **Florida
Test**

 **Total duration:
12 months**

 **EXPOSURE PERIOD:**

FROM: 13/01/2011

TO: 17/01/2012

LAB. ID NUMBER: 23561
POWDER COATING: Mirror 30
HEAT TRANSFER FILM: 6052/02L
colour variation (ΔE): 0,74
residual gloss: 75%

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE)

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS
The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

