

 **Florida
Test**

 **Total duration:
12 months**

 **EXPOSURE PERIOD:**

FROM: 20/04/2015

TO: 09/05/2016

LAB. ID NUMBER: 36677
POWDER COATING: 9C-035-A001
HEAT TRANSFER FILM: 1404/02
Colour variation (ΔE): **1,05**
residual gloss: **91%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS
The residual gloss shall be at least 50% of the original gloss.
The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

