



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 25/01/2016

TO: 25/01/2017

LAB. ID NUMBER: 32827
POWDER COATING: DS 1733
HEAT TRANSFER FILM: 1806/03
Colour variation (ΔE): **2,39**
residual gloss: 93%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area
(reference)**

**Exposed
area**

