



Florida  
Test



Total duration:  
12 months



EXPOSURE PERIOD:

FROM: 27/11/2015

TO: 19/12/2016

LAB. ID NUMBER: 38585  
POWDER COATING: MirrorBT-058S  
HEAT TRANSFER FILM: 2120/01  
Colour variation ( $\Delta E$ ): 8,08  
residual gloss: 100%

### Technical Remarks

Residual gloss is excellent but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

**Not for outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

### REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

