



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 21/09/2021

TO: 20/10/2022

LAB. ID NUMBER: 50952
POWDER COATING: Mirror-188S
HEAT TRANSFER FILM: 6029/06
Colour variation (ΔE): 0,4
residual gloss: 85%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area
(reference)**

**Exposed
area**

