



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 01/05/2021**

**TO: 01/05/2022**

LAB. ID NUMBER: 50538  
POWDER COATING: 9G-233-A005  
HEAT TRANSFER FILM: 2117/23  
colour variation ( $\Delta E$ ): 1,55  
residual gloss: 51%

**Technical Remarks**

Sufficient residual gloss and normal colour variation  
( $\Delta E$ )

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

