



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 07/08/2012

TO: 06/08/2013

LAB. ID NUMBER: 27399
POWDER COATING: DS 402
HEAT TRANSFER FILM: 1404/02
colour variation (ΔE): 3,34
residual gloss: 74%

Technical Remarks

Residual gloss is sufficient but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

