



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 25/11/2013**

**TO: 25/11/2014**

LAB. ID NUMBER: 32855  
POWDER COATING: DS 1791D  
HEAT TRANSFER FILM: 2531/03  
Colour variation ( $\Delta E$ ): 0,72  
residual gloss: 92%

**Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

