



**Florida
Test**



**Total duration:
12 month**



EXPOSURE PERIOD:

FROM: 07/08/2012

TO: 06/08/2013

LAB. ID NUMBER: 27436
POWDER COATING: DS 402
HEAT TRANSFER FILM: 2501/05
Colour variation (ΔE): **1,24**
residual gloss: **95%**

Technical Remarks

Excellent residual gloss and very low colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

