



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 19/01/2018**

**TO: 24/01/2019**

LAB. ID NUMBER: 41569  
POWDER COATING: DS 445  
HEAT TRANSFER FILM: 2501/05  
Colour variation ( $\Delta E$ ): 3,28  
residual gloss: 51%

#### **Technical Remarks**

Residual gloss is sufficient but visual colour variation  
is not acceptable for outdoor use.

**Technical opinion:**

**Not for outdoor use**

Test was carried on samples prepared according to technical  
specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with  
the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

