



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 07/08/2012

TO: 06/08/2013

LAB. ID NUMBER: 27576
POWDER COATING: DS 739
HEAT TRANSFER FILM: 2502/01
Colour variation (ΔE): **1,58**
residual gloss: 75%

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).



**Unexposed area
(reference)**

**Exposed
area**

