



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: 20/04/2015

TO: 09/05/2016

LAB. ID NUMBER: 36631
POWDER COATING: DS 442
HEAT TRANSFER FILM: 2121/02
Colour variation (ΔE): 2,26
residual gloss: 100%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Unexposed area
(reference)

Exposed
area

