

Florida Test



Total duration: 12 months



EXPOSURE PERIOD:

FROM: 01/05/2021

> TO: 01/05/2022

LAB. ID NUMBER: 50085 POWDER COATING: 8G-007-A005 HEAT TRANSFER FILM: 2302/01 colour variation (ΔE): 1,87 residual gloss: 68%

Technical Remarks

Sufficient residual gloss and normal colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye

