



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 13/01/2011**

**TO: 17/01/2012**

LAB. ID NUMBER: 23525  
POWDER COATING: DS 733  
HEAT TRANSFER FILM: 1412/03L  
colour variation ( $\Delta E$ ): 2,58  
residual gloss: 52%

#### **Technical Remarks**

Sufficient residual gloss and very low colour variation ( $\Delta E$ )

#### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

