



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 27/04/2019

TO: 07/05/2020

LAB. ID NUMBER: 44198
POWDER COATING: DS 421
HEAT TRANSFER FILM: 1401/01
Colour variation (ΔE): 3,12
residual gloss: 60%

Technical Remarks

Sufficient residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye.

