



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 07/08/2012

TO: 06/08/2013

LAB. ID NUMBER: 27556
POWDER COATING: DS 721
HEAT TRANSFER FILM: 1403/01
colour variation (ΔE): 1,62
residual gloss: 65%

Technical Remarks

Sufficient residual gloss and very low colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical
specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with
the naked eye, with a maximum value of 4 on the grey scale
(ISO 105-A02).

**Unexposed area
(reference)**

**Exposed
area**

