



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 19/01/2018

TO: 24/01/2019

LAB. ID NUMBER: 41626
POWDER COATING: DS 1733
HEAT TRANSFER FILM: 1501/03
Colour variation (ΔE): **1,85**
residual gloss: **67%**

Technical Remarks

Good residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area
(reference)**

**Exposed
area**

