



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 01/05/2021**

**TO: 01/05/2022**

LAB. ID NUMBER: 50438  
POWDER COATING: DS-0716S  
HEAT TRANSFER FILM: 2507/07  
colour variation ( $\Delta E$ ): 1,06  
residual gloss: 96%

### **Technical Remarks**

Excellent residual gloss and normal colour variation  
( $\Delta E$ )

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with  
the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

