


 **Florida  
Test**

 **Total duration:  
12 months**

 **EXPOSURE PERIOD:**  
  
**FROM: 20/04/2015**  
  
**TO: 09/05/2016**

LAB. ID NUMBER: 36610  
POWDER COATING: DS 406  
HEAT TRANSFER FILM: 2503/04  
Colour variation ( $\Delta E$ ): 1,71  
residual gloss: 99%

**Technical Remarks**  
  
Excellent residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**  
**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALICOAT REQUIREMENTS**  
The residual gloss shall be at least 50% of the original gloss.  
The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

