



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 10/01/2012**

**TO: 10/01/2013**

LAB. ID NUMBER: 25608  
POWDER COATING: DS-0402S  
HEAT TRANSFER FILM: 1440/01  
Colour variation ( $\Delta E$ ): **1,98**  
residual gloss: **100%**

**Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).



**Unexposed area  
(reference)**

**Exposed  
area**

