



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 19/01/2018

TO: 24/01/2019

LAB. ID NUMBER: 41660
POWDER COATING: DS 733
HEAT TRANSFER FILM: 1001/03
Colour variation (ΔE): **2,17**
residual gloss: **72%**

Technical Remarks

Good residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

