



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **19/01/2018**

TO: **24/01/2019**

LAB. ID NUMBER: 41661
POWDER COATING: DS 733
HEAT TRANSFER FILM: 1441/01
Colour variation (ΔE): **1,92**
residual gloss: 73%

Technical Remarks

Good residual gloss and normal colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

