



**Florida  
Test**



**Total duration:**  
12 months



From **22/06/2012** to **21/06/2013**



**Florida  
Test**



**Total duration:**  
36 months



From **22/06/2012** to **25/06/2015**

**Unexposed  
area  
(reference)**

**Exposed  
area**



**Unexposed  
area  
(reference)**

**Exposed  
area**



LAB. ID NUMBER: 24936  
POWDER COATING: DS-0401S  
HEAT TRANSFER FILM: 82505/06 L4  
Colour variation ( $\Delta E$ ): **1,23**  
residual gloss: **98%**

**Approved  
combination:**



LAB. ID NUMBER: 24994  
POWDER COATING: DS-0401S  
HEAT TRANSFER FILM: 82505/06 L4  
Colour variation ( $\Delta E$ ): **2,81**  
residual gloss: **55%**

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).