



Florida
Test



Total duration:
12 months



Florida
Test



Total duration:
36 months



From **22/06/2012** to **21/06/2013**



From **22/06/2012** to **25/06/2015**

Unexposed
area
(reference)

Exposed
area



Unexposed
area
(reference)

Exposed
area



LAB. ID NUMBER: 24939
POWDER COATING: DS-0402S
HEAT TRANSFER FILM: 81501/02 L4
Colour variation (ΔE): **1,24**
residual gloss: **100%**

Approved
combination:



LAB. ID NUMBER: 24997
POWDER COATING: DS-0402S
HEAT TRANSFER FILM: 81501/02 L4
Colour variation (ΔE): **2,67**
residual gloss: **92%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).