



Florida
Test



Total duration:
12 months



Florida
Test



Total duration:
36 months



From **22/06/2012** to **21/06/2013**



From **22/06/2012** to **25/06/2015**

Unexposed
area
(reference)

Exposed
area



Unexposed
area
(reference)

Exposed
area



LAB. ID NUMBER: 24941
POWDER COATING: DS-0421S
HEAT TRANSFER FILM: 81403/01 L4
Colour variation (ΔE): 0,85
residual gloss: 100%

Approved
combination:



LAB. ID NUMBER: 24999
POWDER COATING: DS-0421S
HEAT TRANSFER FILM: 81403/01 L4
Colour variation (ΔE): 2,9
residual gloss: 100%

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).