



Florida
Test



Total duration:
12 months



From **09/09/2020** to **26/10/2021**



Florida
Test



Total duration:
36 months



From **09/09/2020** to **16/10/2023**

Unexposed
area
(reference)

Exposed
area



Unexposed
area
(reference)

Exposed
area



LAB. ID NUMBER: 47906
POWDER COATING: DS-0706S
HEAT TRANSFER FILM: 82504/01 L4
Colour variation (ΔE): 0,95
residual gloss: 98%

Approved
combination:



LAB. ID NUMBER: 48202
POWDER COATING: DS-0706S
HEAT TRANSFER FILM: 82504/01 L4
Colour variation (ΔE): 3,04
residual gloss: 57%

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).