



Florida
Test



Total duration:
12 months



From **09/09/2020** to **26/10/2021**



Florida
Test



Total duration:
36 months



From **09/09/2020** to **16/10/2023**

Unexposed
area
(reference)

Exposed
area



Unexposed
area
(reference)

Exposed
area



LAB. ID NUMBER: 47943
POWDER COATING: DS-0721S
HEAT TRANSFER FILM: 81402/02 L4
Colour variation (ΔE): 0,68
residual gloss: 94%

Approved
combination:



LAB. ID NUMBER: 48239
POWDER COATING: DS-0721S
HEAT TRANSFER FILM: 81402/02 L4
Colour variation (ΔE): 2,32
residual gloss: 51%

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).