




Florida  
Test



Total duration:  
12 months



From **09/09/2020** to **26/10/2021**




Florida  
Test



Total duration:  
36 months



From **09/09/2020** to **16/10/2023**



LAB. ID NUMBER: 47954  
POWDER COATING: DS-0721S  
HEAT TRANSFER FILM: 81704/01 L4  
Colour variation ( $\Delta E$ ): **1,07**  
residual gloss: **99%**

Approved  
combination:



LAB. ID NUMBER: 48250  
POWDER COATING: DS-0721S  
HEAT TRANSFER FILM: 81704/01 L4  
Colour variation ( $\Delta E$ ): **2,87**  
residual gloss: **53%**

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).