



**Florida
Test**



Total duration:
12 months



From **09/09/2020** to **26/10/2021**



**Florida
Test**



Total duration:
36 months



From **09/09/2020** to **16/10/2023**

**Unexposed
area
(reference)**

**Exposed
area**



**Unexposed
area
(reference)**

**Exposed
area**



LAB. ID NUMBER: 47983
POWDER COATING: DS-0731S
HEAT TRANSFER FILM: 82513/11 L8
Colour variation (ΔE): **0,79**
residual gloss: **100%**

**Approved
combination:**



LAB. ID NUMBER: 48279
POWDER COATING: DS-0731S
HEAT TRANSFER FILM: 82513/11 L8
Colour variation (ΔE): **1,76**
residual gloss: **62%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).