




Florida
Test



Total duration:
12 months



From **09/09/2020** to **26/10/2021**




Florida
Test



Total duration:
36 months



From **09/09/2020** to **16/10/2023**



LAB. ID NUMBER: 47989
POWDER COATING: DS-0734S
HEAT TRANSFER FILM: 81304/02 L8
Colour variation (ΔE): **0,39**
residual gloss: **97%**

Approved
combination:



LAB. ID NUMBER: 48285
POWDER COATING: DS-0734S
HEAT TRANSFER FILM: 81304/02 L8
Colour variation (ΔE): **1,58**
residual gloss: **83%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).