


 **Florida  
Test**

 **Total duration:  
12 months**


 From **22/06/2012 to 21/06/2013**



 **Florida  
Test**

 **Total duration:  
36 months**

 From **22/06/2012 to 25/06/2015**



LAB. ID NUMBER: 24955  
POWDER COATING: DS-0734S  
HEAT TRANSFER FILM: 82501/15 L8  
Colour variation ( $\Delta E$ ): 0,26  
residual gloss: 92%

Approved  
combination:  


LAB. ID NUMBER: 25013  
POWDER COATING: DS-0734S  
HEAT TRANSFER FILM: 82501/15 L8  
Colour variation ( $\Delta E$ ): 0,99  
residual gloss: 70%

**QUALICOAT REQUIREMENTS**  
The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**  
The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).