




**Florida
Test**



**Total duration:
12 months**



From **09/09/2020** to **26/10/2021**




**Florida
Test**



**Total duration:
36 months**



From **09/09/2020** to **16/10/2023**



LAB. ID NUMBER: 48001
POWDER COATING: DS-0742S
HEAT TRANSFER FILM: 81416/01 L4
Colour variation (ΔE): **0,76**
residual gloss: **97%**

Approved
combination:



LAB. ID NUMBER: 48297
POWDER COATING: DS-0742S
HEAT TRANSFER FILM: 81416/01 L4
Colour variation (ΔE): **2,29**
residual gloss: **55%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).