

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss. The ΔE values not greater than 65% of the limits in the table (see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss. The ΔE values within the limits prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Date: 05/12/2024