




Florida
Test



Total duration:
12 months



From **09/09/2020** to **26/10/2021**




Florida
Test



Total duration:
36 months



From **09/09/2020** to **16/10/2023**



LAB. ID NUMBER: 48056
POWDER COATING: DS-0772S
HEAT TRANSFER FILM: 82507/18 L4
Colour variation (ΔE): **1,05**
residual gloss: **98%**

Approved
combination:



LAB. ID NUMBER: 48352
POWDER COATING: DS-0772S
HEAT TRANSFER FILM: 82507/18 L4
Colour variation (ΔE): **1,94**
residual gloss: **53%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).