



Florida  
Test



Total duration:  
12 months



From **22/06/2012** to **21/06/2013**



Florida  
Test



Total duration:  
36 months



From **22/06/2012** to **25/06/2015**

Unexposed  
area  
(reference)

Exposed  
area



Unexposed  
area  
(reference)

Exposed  
area



LAB. ID NUMBER: 24960  
POWDER COATING: MirrorBT-022S  
HEAT TRANSFER FILM: 85007/01 L4  
Colour variation ( $\Delta E$ ): **1,74**  
residual gloss: **98%**

Approved  
combination:



LAB. ID NUMBER: 25018  
POWDER COATING: MirrorBT-022S  
HEAT TRANSFER FILM: 85007/01 L4  
Colour variation ( $\Delta E$ ): **2,57**  
residual gloss: **75%**

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).