



Florida
Test



Total duration:
12 months



Florida
Test



Total duration:
36 months



From **22/06/2012** to **21/06/2013**



From **22/06/2012** to **25/06/2015**

Unexposed
area
(reference)

Exposed
area



Unexposed
area
(reference)

Exposed
area



LAB. ID NUMBER: 24961
POWDER COATING: Mirror-073S
HEAT TRANSFER FILM: 81401/01 L4
Colour variation (ΔE): **0,52**
residual gloss: **95%**

Approved
combination:



LAB. ID NUMBER: 25019
POWDER COATING: Mirror-073S
HEAT TRANSFER FILM: 81401/01 L4
Colour variation (ΔE): **1,75**
residual gloss: **57%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).