


 **Florida
Test**

 **Total duration:
12 months**

 From **22/06/2012 to 21/06/2013**



 **Florida
Test**

 **Total duration:
36 months**

 From **22/06/2012 to 25/06/2015**



LAB. ID NUMBER: 25879
POWDER COATING: DS-0402S
HEAT TRANSFER FILM: 82501/05 L4
Colour variation (ΔE): **0,88**
residual gloss: **100%**

Approved
combination:


LAB. ID NUMBER: 25984
POWDER COATING: DS-0402S
HEAT TRANSFER FILM: 82501/05 L4
Colour variation (ΔE): **1,97**
residual gloss: **86%**

QUALICOAT REQUIREMENTS
The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS
The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).