


 **Florida
Test**

 **Total duration:
12 months**


 **From 05/10/2012 to 04/10/2013**



 **Florida
Test**

 **Total duration:
36 months**

 **From 05/10/2012 to 08/10/2015**



LAB. ID NUMBER: 25924
POWDER COATING: Mirror-058S
HEAT TRANSFER FILM: 85001/01 L8
Colour variation (ΔE): 0,09
residual gloss: 99%

Approved
combination:


LAB. ID NUMBER: 26029
POWDER COATING: Mirror-058S
HEAT TRANSFER FILM: 85001/01 L8
Colour variation (ΔE): 0,8
residual gloss: 71%

QUALICOAT REQUIREMENTS
The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS
The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).