



Florida
Test



Total duration:
12 months



From **05/10/2012** to **04/10/2013**



Florida
Test



Total duration:
36 months



From **05/10/2012** to **08/10/2015**



LAB. ID NUMBER: 25925
POWDER COATING: Mirror-058S
HEAT TRANSFER FILM: 85001/02 L8
Colour variation (ΔE): **0,49**
residual gloss: **97%**

Approved
combination:



LAB. ID NUMBER: 26030
POWDER COATING: Mirror-058S
HEAT TRANSFER FILM: 85001/02 L8
Colour variation (ΔE): **0,84**
residual gloss: **74%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).