



Florida
Test



Total duration:
12 months



Florida
Test





Total duration:
36 months



From **05/10/2012** to **04/10/2013**



From **05/10/2012** to **08/10/2015**



LAB. ID NUMBER: 25927
POWDER COATING: Mirror-058S
HEAT TRANSFER FILM: 85014/03 L8
Colour variation (ΔE): 0,65
residual gloss: 96%

Approved
combination:



LAB. ID NUMBER: 26032
POWDER COATING: Mirror-058S
HEAT TRANSFER FILM: 85014/03 L8
Colour variation (ΔE): 1,47
residual gloss: 81%

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).