



**Florida
Test**



Total duration:
12 months



From **05/10/2012** to **04/10/2013**



**Florida
Test**



Total duration:
36 months



From **05/10/2012** to **08/10/2015**

**Unexposed
area
(reference)**

**Exposed
area**



**Unexposed
area
(reference)**

**Exposed
area**



LAB. ID NUMBER: 25929
POWDER COATING: Mirror-073S
HEAT TRANSFER FILM: 85007/01 L4
Colour variation (ΔE): **1,29**
residual gloss: **100%**

**Approved
combination:**



LAB. ID NUMBER: 26034
POWDER COATING: Mirror-073S
HEAT TRANSFER FILM: 85007/01 L4
Colour variation (ΔE): **2,91**
residual gloss: **67%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).