



Florida  
Test



Total duration:  
12 months



Florida  
Test



Total duration:  
36 months



From **05/10/2012** to **04/10/2013**



From **05/10/2012** to **08/10/2015**

Unexposed  
area  
(reference)

Exposed  
area



Unexposed  
area  
(reference)

Exposed  
area



LAB. ID NUMBER: 25930  
POWDER COATING: Mirror-073S  
HEAT TRANSFER FILM: 86048/02 L4  
Colour variation ( $\Delta E$ ): **1,29**  
residual gloss: **90%**

Approved  
combination:



LAB. ID NUMBER: 26035  
POWDER COATING: Mirror-073S  
HEAT TRANSFER FILM: 86048/02 L4  
Colour variation ( $\Delta E$ ): **1,82**  
residual gloss: **58%**

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**

The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).