


 Florida  
Test

 Total duration:  
12 months


 From **05/10/2012** to **04/10/2013**



 Florida  
Test

 Total duration:  
36 months

 From **05/10/2012** to **08/10/2015**



LAB. ID NUMBER: 25941  
POWDER COATING: MirrorL-183S  
HEAT TRANSFER FILM: 86053/01 L4  
Colour variation ( $\Delta E$ ): **0,34**  
residual gloss: **100%**

Approved  
combination:  


LAB. ID NUMBER: 26046  
POWDER COATING: MirrorL-183S  
HEAT TRANSFER FILM: 86053/01 L4  
Colour variation ( $\Delta E$ ): **1,46**  
residual gloss: **100%**

**QUALICOAT REQUIREMENTS**  
The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**  
The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).