


 **Florida
Test**

 **Total duration:
12 months**

 **From 15/07/2013 to 17/07/2014**



 **Florida
Test**

 **Total duration:
36 months**

 **From 15/07/2013 to 15/07/2016**



LAB. ID NUMBER: 30787
POWDER COATING: DS-0402S
HEAT TRANSFER FILM: 81502/02 L4
Colour variation (ΔE): **0,23**
residual gloss: **99%**

Approved
combination:


LAB. ID NUMBER: 31144
POWDER COATING: DS-0402S
HEAT TRANSFER FILM: 81502/02 L4
Colour variation (ΔE): **1,52**
residual gloss: **85%**

QUALICOAT REQUIREMENTS
The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS
The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).