


 **Florida  
Test**

 **Total duration:  
12 months**


 **From 15/07/2013 to 17/07/2014**



 **Florida  
Test**

 **Total duration:  
36 months**

 **From 15/07/2013 to 15/07/2016**



LAB. ID NUMBER: 30788  
POWDER COATING: DS-0402S  
HEAT TRANSFER FILM: 82118/01 L4  
Colour variation ( $\Delta E$ ): 0,52  
residual gloss: 94%

Approved  
combination:



LAB. ID NUMBER: 31145  
POWDER COATING: DS-0402S  
HEAT TRANSFER FILM: 82118/01 L4  
Colour variation ( $\Delta E$ ): 2,64  
residual gloss: 89%

**QUALICOAT REQUIREMENTS**  
The residual value shall be at least 75% of the original gloss.  
The  $\Delta E$  values not greater than 65% of the limits in the table  
(see Appendix A7 of Qualicoat Specifications).

**QUALICOAT REQUIREMENTS**  
The residual value shall be at least 50% of the original gloss.  
The  $\Delta E$  values within the limits prescribed in the annexed  
table (see Appendix A7 of Qualicoat Specifications).