



Florida
Test



Total duration:
12 months



Florida
Test



Total duration:
36 months



From 15/07/2013 to 17/07/2014



From 15/07/2013 to 15/07/2016

Unexposed
area
(reference)

Exposed
area



Unexposed
area
(reference)

Exposed
area



LAB. ID NUMBER: 30805
POWDER COATING: DS-0421S
HEAT TRANSFER FILM: 81412/03 L4
Colour variation (ΔE): 0,73
residual gloss: 100%

Approved
combination:



LAB. ID NUMBER: 31162
POWDER COATING: DS-0421S
HEAT TRANSFER FILM: 81412/03 L4
Colour variation (ΔE): 2,67
residual gloss: 100%

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).