




**Florida
Test**



Total duration:
12 months



From **15/07/2013** to **17/07/2014**




**Florida
Test**



Total duration:
36 months



From **15/07/2013** to **15/07/2016**



LAB. ID NUMBER: 30834
POWDER COATING: DS-0708S
HEAT TRANSFER FILM: 82505/10 L8
Colour variation (ΔE): **0,67**
residual gloss: **96%**

Approved
combination:



LAB. ID NUMBER: 31191
POWDER COATING: DS-0708S
HEAT TRANSFER FILM: 82505/10 L8
Colour variation (ΔE): **1,18**
residual gloss: **69%**

QUALICOAT REQUIREMENTS

The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS

The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).