


 **Florida
Test**

 **Total duration:
12 months**

 **From 15/07/2013 to 17/07/2014**



 **Florida
Test**

 **Total duration:
36 months**

 **From 15/07/2013 to 15/07/2016**



LAB. ID NUMBER: 30844
POWDER COATING: DS-0721S
HEAT TRANSFER FILM: 81441/01 L4
Colour variation (ΔE): 0,97
residual gloss: 98%

Approved
combination:


LAB. ID NUMBER: 31201
POWDER COATING: DS-0721S
HEAT TRANSFER FILM: 81441/01 L4
Colour variation (ΔE): 2,83
residual gloss: 54%

QUALICOAT REQUIREMENTS
The residual value shall be at least 75% of the original gloss.
The ΔE values not greater than 65% of the limits in the table
(see Appendix A7 of Qualicoat Specifications).

QUALICOAT REQUIREMENTS
The residual value shall be at least 50% of the original gloss.
The ΔE values within the limits prescribed in the annexed
table (see Appendix A7 of Qualicoat Specifications).